



BOSS[®] 201 Screw Locking Compound

TYPICAL PROPERTIES


Monomer (Liquid)

Base Compound Dimethacrylate Ester
 Appearance Purple Liquid
 Viscosity (cP @ 68°F) 1200 cP
 Specific Gravity (g/cc) 1.09
 Gap Fill007"
 Corrosivity None
 Flash Point (TCC) >200°F
 Toxicity Low
 Shelf Life @ 40°F 1 Year Unopened

Polymer (Cured)

Locking Strength Low
 Appearance Purple Solid
 Service Temperature Range -75°F - 300°F
 Full Cure Time 24 Hours
 Shear Strength (steel nuts & bolts) 600 psi

*Information on this data sheet is subject to change without notice and should not be used for writing specifications.
 For additional information on specific applications, contact Accumetric, LLC



PERFORMANCE OF CURED MATERIALS

Bond strength after 24 hours at 69°F to 78°F (20°C to 25°C) on steel nuts and bolts.

	Average Value	Range
Breakaway Torque	58 in. lbs.	25-80 in. lbs.
Prevailing Torque	30 in. lbs.	10-50 in. lbs.

DESCRIPTION

BOSS[®] 201 Screw Locking Compound is a single component, anaerobic threadlocking adhesive, which is thixotropic and develops low strength. The product cures between close fitting metal parts where there is an absence of air.

CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

FEATURES

- Meets Military Specification Mil-S-46163A, Type II, Grade M
- Prevents loosening from vibration and leakage of threaded fasteners
- Suitable for applications where easy disassembly is required

SETTING TIME (68°F, 65% RH)

Substrate Set Time / Full Cure
 Steel 15 minutes / 24 hours
 Brass 20 minutes / 24 hours
 Zn Dichromate 30 minutes / 24 hours
 Stainless Steel 40 minutes / 24 hours

HOW TO USE

Surfaces to be bonded should be clean, dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.


CHEMICAL RESISTANCE

Sheer strength on steel after 500 hours

Solvent	% Strength Retained
Motor Oil	100
Unleaded Gasoline	95
Trichloroethane	90
Brake Fluid	95
Ethanol	95
Acetone	95
Water/Glycol Mix	80

TEMPERATURE RESISTANCE

% Retained strength when tested at temperature



PACKAGING

BOSS® 200 is available in 50ml and 250ml bottles.

SHIPPING LIMITATIONS

None.
Reactive VOC 127 g/l

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **BOSS® 201** Screw Locking Compound has a shelf life of 12 months from date of shipment. In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity.

Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

CAUTION

DIRECT CONTACT OF UNCURED PRODUCT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use with adequate ventilation. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

BOSS® PRODUCTS

Accumetric, LLC
350 Ring Road
Elizabethtown,
Kentucky 42701 USA
800-928-BOSS(2677)
TEL (270)769-3385
FAX (270)765-2412
Outside U.S.
TEL +1(270)769-3385
FAX +1(270)765-2412

Accumetric Asia Pacific, LTD
18 Kitpanit Bldg, 5th Floor
#502 Patpong Road
Suriyawong, Bangrak
Bangkok, 10500 Thailand
TEL (662)634-3060
FAX (662)634-3066

www.bossproducts.com