



## BOSS<sup>®</sup> 209 Gap Filling Retaining Compound

### TYPICAL PROPERTIES

#### Monomer (Liquid)

Base Compound .....	Dimethacrylate Ester
Appearance .....	Green Liquid
Viscosity (cP @ 68°F) .....	7000 cP
Specific Gravity (g/cc) .....	1.10
Gap Fill .....	.016"
Corrosivity .....	None
Flash Point (TCC) .....	>200°F
Toxicity .....	Low
Shelf Life @ 40°F .....	1 Year Unopened

#### Polymer (Cured)

Retaining Strength .....	High
Appearance .....	Green Solid
Service Temperature Range .....	-75°F - 464°F
Full Cure Time .....	24 Hours
Shear Strength (steel nuts and bolts) .....	3600 psi

\*Information on this data sheet is subject to change without notice and should not be used for writing specifications.  
For additional information on specific applications, contact Accumetric, LLC



### PERFORMANCE OF CURED MATERIALS

Bond strength after 24 hours at 69°F to 78°F (20°C to 25°C) on steel.  
Shear Strength 2700-3600 psi.

### DESCRIPTION

**BOSS<sup>®</sup> 209** Gap Filling Retaining Compound is a single component anaerobic retaining and locking adhesive, which develops high strength and heat resistance. The product cures between close fitting metal parts where there is an absence of air.

### CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

### FEATURES

- Can be applied to retain pulleys, gears, rotors and shafts
- Secures bushings, bearings and housing plugs
- Will augment shrink and press fit assemblies in high heat and high friction environments

### SETTING TIME (68°F, 65% RH)

<b>Substrate</b> .....	<b>Set Time / Full Cure</b>
Steel .....	60-120 minutes / 24 hours
Zn Dichromate .....	60-120 minutes / 24 hours
Aluminum .....	60-120 minutes / 24 hours

## HOW TO USE

Surfaces to be bonded should be clean, dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

**This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.


## CHEMICAL RESISTANCE

Shear strength on steel after 500 hours

Solvent .....	% Strength Retained
Motor Oil .....	100
Unleaded Gasoline .....	95
Brake Fluid .....	100
Ethanol .....	100
Acetone .....	95
Water/Glycol Mix .....	80

## TEMPERATURE RESISTANCE

% Retained strength when tested at temperature



## PACKAGING

**BOSS® 209** is available in 50ml and 250ml bottles.

## SHIPPING LIMITATIONS

None.  
Reactive VOC 91 g/l

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **BOSS® 209** Gap Filling Retaining Compound has a shelf life of 12 months from date of shipment. In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity.

Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

## CAUTION

DIRECT CONTACT OF UNCURED PRODUCT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use with adequate ventilation. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

## BOSS® PRODUCTS

Accumetric, LLC  
350 Ring Road  
Elizabethtown,  
Kentucky 42701 USA  
800-928-BOSS(2677)  
TEL (270)769-3385  
FAX (270)765-2412  
Outside U.S.  
TEL +1 (270)769-3385  
FAX +1 (270)765-2412

Accumetric Asia Pacific, LTD  
18 Kitpanit Bldg, 5th Floor  
#502 Patpong Road  
Suriyawong, Bangrak  
Bangkok, 10500 Thailand  
TEL (662)634-3060  
FAX (662)634-3066

[www.bossproducts.com](http://www.bossproducts.com)