

RED ANAEROBIC GASKET MAKER PART NO. 49477

PHYSICAL PROPERTIES

Monomer (Liquid)

Base Compound Dimethacrylate Ester
 Appearance..... Red Paste
 Viscosity (cP @ 68°F)..... 110,000 cP
 Specific Gravity (g/cc)..... 1.12
 Gap Fill016"
 Flash Point (TCC) >200°F
 Shelf Life @ 40°F..... 1 year unopened
 Military Specifications None

Polymer (Cured)

Appearance..... Red Solid
 Hardness 47 (JIS D)
 Elongation 100%
 Service Temperature Range -58°F to 302°F
 Full Cure Time..... 24 Hours
 Tensile Strength..... 18.6 Mpa (190Kgf/cm²)
 Shear Strength..... 6.1 Mpa (62Kgf/cm²)
 (A2024P 25°Cx725h)

DESCRIPTION

Dynatex® Anaerobic Gasket Maker is a single component, medium strength thixotropic anaerobic sealant, which develops medium strength. The product cures between close fitting metal parts where there is an absence of air. It provides a tough, resilient, solvent and temperature resistant seal that flexes with flange movement caused by vibration, pressurization or thermal changes.

FEATURES

- No mixing
- No curing outside of joint
- Non-corrosive to aluminum or cast iron parts
- Eliminates need to re-torque compressible mechanical gaskets

TYPICAL APPLICATIONS

- Vacuum pump flanges
- Fuel pumps
- Water pumps
- Gearbox covers
- Automotive and truck axle covers
- Split crankcases
- Thermostats

CURING PROPERTIES

The rate of cure will depend on environmental conditions and the substrates used. *Dynatex® Anaerobic Gasket Maker* will offer an instant seal while still uncured when subjected to a low on-line pressure test.

CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

PERFORMANCE OF CURED MATERIALS PRESSURE RESISTANCE

Specification: JIS-K-6820
 Bolt Type: M10 Number Samples: 8
 Fastening Force: 150 Kgf-cm
 Blow Out Test: 5 Minutes after Assembly
 Heat Cycle: -30°C x 1Hr. → 25°C x 30 min.
 → 130°C x 1Hr. Cycle repeated 100 times.
 Pressure Conditions: 0.98 Mpa/min.

SETTING TIME (68°F, 65% R.H.)

Substrate	Set time/Full cure
Steel	30-60 min/24 hrs
Aluminum	30-60 min/24 hrs

Lap Shear at Varying Time and Temperature

	15 Min.	30 Min.	1 Hr	3 Hrs	8 Hrs
5°C	13.6	24.5	31.5	43.8	49.7
25°C	32.0	36.2	53.5	58.2	60.4

Chemical Resistance

Shear strength on steel after 500 hours

Solvent	% Strength Retained
Motor Oil	100
Unleaded Gasoline	95
Brake Fluid	100
Ethanol	100
Acetone	95
Water/Glycol Mix	80

Oil Resistance

	Lap Shear (Kgf/ cm ²)	Conditions
ATF	96.4	120°C x 240h D-III
Engine Oil	119.1	150°C x 240h 5W-30SH
Gear Oil	75.7	120°C x 240h 75W-90

GENERAL INSTRUCTIONS

Surfaces to be bonded should be clean and dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps, which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® Anaerobic Gasket Maker** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it the user's responsibility to determine suitable of use. Since the supplier cannot know all the uses, or the conditions of use to which there products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

The supplier warrants only that its products will meet its specifications. There is no use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product when to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® A division of Accumetric, LLC

Dynatex
350 Ring Road
Elizabethtown
Kentucky 42701 USA
(800) 999-2937
TEL (270) 769-5557
FAX (270) 769-6418
Outside U.S.
TEL +1(270) 769-5557
FAX +1(270) 769-6418

Accumetric Asia Pacific, LTD
18 Kitpanit Bldg. 5th Floor
#502 Patpong Road
Suriyawong, Bangrak
Bangkok, 10500 Thailand
TEL (662) 634-3060
FAX (662) 634-3066

Email: sales@dynatexinc.com
Website: www.dynatexinc.com