# Safety Data Sheet BOSS© 399 Moisture Curing Silicone Sealant

## Section 1. Identification

Product Identifier Synonyms Manufacture Stock Numbers	BOSS© 399 Moisture Cu N/A N/A	ring Silicone Sea	lant
Recommended use Uses advised against	Refer to Technical Data Refer to Technical Data		
Manufacturer Contact Address	SOUDAL Accumetric 350 Ring Road Elizabethtown, KY, 4270 USA	)1	
	Phone	Emergency Phone	Fax
	(270) 769-3385	(800) 424-	N/A

## Section 2. Hazards Identification

Classification	EYE DAMAGE/IRRITATION - Category 2A HAZARDOUS TO THE AQUATIC ENVIROMENT - LONG-TERM HAZARD - Category 3 SENSITIZATION - SKIN - Category 1 SPECIFIC TARGET ORGAN TOXICITY (Repeated Exposure) - Category 2
Signal Word	Warning
Pictogram	
Hazard Statements	Causes serious eye irritation Harmful to aquatic life with long lasting effects May cause an allergic skin reaction May cause damage to organs through prolonged or repeated exposure.
Precautionary Statements	
Response	Get medical advice/attention if you feel unwell.

9300 Chemtrec

	If eye irritation persists: Get medical advice/attention. If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If on skin: Wash with plenty of soap and water. Wash contaminated clothing before reuse. If skin irritation or rash occurs: Get medical advice/attention. Wash contaminated clothing before reuse.
Prevention	Avoid breathing dust/fume/gas/mist/ vapors/spray. Avoid release to the environment Contaminated work clothing must not be allowed out of the workplace. Do not breathe dust/fume/gas/mist/ vapors/spray. Wash hands thoroughly after handling. Wear eye protection/face protection. Wear protective gloves.
Storage	N/A
Disposal	Dispose of contents and container in accordance with all local, regional, national and international regulations.

Ingredients of unknown 0% toxicity

Hazards not Otherwise None known Classified

## Section 3. Ingredients

CAS	Ingredient Name	Weight %
1760-24-3	N-beta-(aminoethyl)-gamma-aminopropyltrimethoxysilane	1% - 5%
2224-33-1	Vinyl Oximino Silane	1% - 5%
22984-54-9	Methyl Oximino Silane	1% - 5%
63148-62-9	Dimethylpolysiloxane	10% - 30%
112945-52-5	Amorphous fumed silica	5% - 10%
64741-44-2	Distillates (petroleum), straight-run middle	5% - 10%

Occupational exposure limits, if available, are listed in Section 8.

#### Section 4. First-aid Measures

Inhalation	Remove to fresh air. If symptoms persist, obtain appropriate medical attention.
Ingestion	Get medical attention.
Comments	Treat according to person's condition and specifics of exposure.

## Section 5. Fire Fighting Measures

Suitable Extinguishing Media Unsuitable Extinguishing Media Auto-ignition Temperature Flammability Limits in Air Extinguishing Media N/A

N/A

Not determined

Not determined

On large fires use dry chemical, foam, or water spray. On small fires use carbon dioxide, dry chemical or water spray. Water can be used to cool fire exposed containers. None known

Unusual Fire or Explosion Hazards

#### Section 6. Accidental Release Measures

Containment/Clean Up Observe all personal protective equipment recommendations as described in section eight. Collecr all spilled materials for disposal. This material is not classified as a hazardous waste per 40 CFR 261. State and local laws may impose regulatory restrictions.

#### Section 7. Handling and Storage

Handling
Avoid breathing vapors in top of shipping container. Keep container closed. Use with adequate ventilation. Avoid contact with skin and clothing. Wash throughly after handling.
Storage
Keep container closed and store in a cool, well ventilated area, away from water or moisture.

## Section 8. Exposure Controls/Personal Protecction

Occupational Exposure	Ingredient Name	ACGIH	OSHA	STEL
Limits		TLV	PEL	STEE
	N-beta-(aminoethyl)-gamma-	N/A	N/A	N/A
	aminopropyltrimethoxysilane			
	Vinyl Oximino Silane	N/A	N/A	N/A
	Methyl Oximino Silane	N/A	N/A	N/A
	Dimethylpolysiloxane	10	6	N/A
		mg/m3	mg/m3	
	Amorphous fumed silica	N/A	N/A	N/A
	Distillates (petroleum), straight-run	N/A	N/A	N/A
	middle			
Personal Protective Equipment	N/A			
Ventilation	Local and general ventilation are recomm	ended.		
Respiratory Protection	If engineering controls do not maintain airborne concentrations of hazardous ingredients below TLV, then a NIOSH/MSHA approved organic vapor respirator should be used.			
Eye Protection	Wear safety glasses with side shields as a minimum.			
Skin Protection	Impervious gloves are suggested. Wash at mealtimes and end of shift.			
Other Limits	Methyl Oximino Silane (22984-54-9) Methyl Ethyl Ketoxime is formed upon contact with water of moisture in the air. Provide adequate ventilation to control exposures within the exposure guideline of AIHA 10 ppm (STEL) and ACGIH 10 ppm (TWA). It is recommended that concentrations of MEKO be kept below 3 ppm (TWA). Average exposures to MEKO have been measured at 3 ppm or less for typical applications. N-beta-(aminoethyl)-gamma- aminopropyltrimethoxysilane (1760-24-3) Methanol may be formed by reaction with moisture in the air. Provide adequate ventilation to control exposure within the guidelines of OSHA TWA 200 ppm.			

## Section 9. Physical and Chemical Properties

Physical StatePasteColorSee product labelOdorSlightOdor ThresholdNot availableSolubilityNegligiblePartition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3 Density Ibs/GalDensity Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AEvaporation RateNot availableFlammabilityNot availableFlammabilityNot availablePortion TemperatureNot availableVapor PressureNot availableVapor DensityNot availableVapor DensityNot available		
IabeiOdorSlightOdor ThresholdNot availableSolubilityNegligiblePartition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3 Density Ibs/GalPounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AEvaporation RateNot availableFlammabilityNot availableFlammabilityNot availableBoiling RangeN/ALeLN/AVapor PressureNot availableVapor DensityNot		
Odor ThresholdNot availableSolubilityNegligiblePartition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot	Color	
Odor ThresholdNot availableSolubilityNegligiblePartition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot	Odor	Slight
SolubilityNegligiblePartition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3 Density Ibs/GalDensity Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot	Odor Threshold	
Partition coefficient Water/n- octanolNot availableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot availableVapor DensityNot		available
octanolavailableViscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot		Negligible
Viscosity10,000 cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot	Partition coefficient Water/n-	
cm2/s 1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot available		
1,000,000 cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AFlammabilityNot availableFlammabilityNot availableVapor PressureNot availableVapor DensityNot	Viscosity	
cStSpecific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/APlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
Specific Gravity1.3Density Ibs/GalN/APounds per Cubic FootN/APlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
Density Ibs/GalN/APounds per Cubic FootN/APlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Creatific Creatity	
Pounds per Cubic FootN/AFlash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
Flash PointNot availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
availableFP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
FP MethodN/APhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Flash Point	
PhNot applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
applicableMelting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
Melting PointNot availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Ph	
availableBoiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Malting Daint	
Boiling PointNot availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Meiting Point	
availableBoiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Poiling Doint	
Boiling RangeN/ALELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Bolling Politi	
LELN/AUELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Boiling Range	
UELN/AEvaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
Evaporation RateNot availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
availableFlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
FlammabilityNot availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
availableDecomposition TemperatureNot availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Flammability	
Decomposition Temperature Not available Auto-ignition Temperature Not available Vapor Pressure Not available Vapor Density Not	lannaonty	
availableAuto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot	Decomposition Temperature	
Auto-ignition TemperatureNot availableVapor PressureNot availableVapor DensityNot		
availableVapor PressureNot availableVapor DensityNot	Auto-ignition Temperature	
Vapor Density Not		available
Vapor Density Not	Vapor Pressure	Not
		available
available	Vapor Density	Not
		available

NoteThe above information is not intended for use in preparing product specifications. Contact SOUDAL Accumentric before writing specifications.

Section 10. Stability and Reactivity

Chemical Stability	Stable
Hazardous Polymerization	Will not occur
Materials to Avoid / Incompatibility	Oxidizing material can cause a reaction.

## Section 11. Toxicological Information

Carcinogen	No
Teratogens	No
Mutagens	No
Reproductive Toxins	No
Sensitizer	Product releases MEKO, which is a potential skin sensitizer.
Component Toxicology Information	Methyl Ethyl Ketoxime (MEKO) is formed upon contact with water or humid air. Male rodents exposed to MEKO vapor throughout their lifetime developed liver tumors. Since many commonly used chemicals cause liver tumors in rats and mice, additional testing is planned by the MEKO supplier to determine any relevance to humans. Until more data is known, exposure levels should be maintained as low as achievable.

#### Section 12. Ecological Information

Environmental Effects Complete information is not yet available. Fate and Effects in Complete information is not yet available. Waste Water Treatment Plants Environmental Fate and Complete information is not yet available. Distribution

#### Section 13. Disposal

This material is not classified as a hazardous waste per 40 CFR 261. State and local laws may impose regulatory restrictions. Observe all federal, state, and local laws regarding waste disposal.

## Section 14. Transport Information

UN Number	N/A
UN Proper Shipping Name	N/A
DOT Classification	N/A
Packing Group	N/A

DOT Road Shipment Information DOT(USA): Caulking & Glaziers, NOI DOT Hazard Classification: None UN/NA Number: Not applicable Label Required: None Marine Pollutant: None

#### Section 15. Regulatory Information

	The contents of this MSDS comply with the OSHA Hazard Communication Standard 29 CFR 1910.1200.
TSCA Status	All chemical substances found in this product comply with the Toxic Substances Control Act inventory reporting requirements.
SARA Title III Section 302 Extremely Hazardous Substances	None
SARA Title III Section 304 CERCLA Hazardous Substances	one
SARA Title III Section 313 Toxic Chemicals	Methanol (67-56-1)
SARA Title III Section 312 Hazard Class	Acute: Yes Chronic: Yes Fire: No Pressure: No Reactive: No
Canada Domestic Substances List	All ingredients are listed on the DSL.
California Proposition 65	This product contains the following chemical(s) listed by the State of California under the Safe Drinking Water and Toxic Enforcement Act of 1986 (Proposition 65) as being known to cause cancer, birth defects or other reproductive harm: None known
Massachusetts	Silica, amorphous fumed (112945-52-5) Methanol (67-56-1)
New Jersey	Hydroxy-terminated polydimethylsiloxane (70131-67-8) Stoddard Solvent (8052-41-3) Aluminatrihydrate (21645-51-2) Polydimethylsiloxane (63148-62-9) Treated silica (67762-90-7) Methyl oximino silane (22984-54-9) Methanol (67-56-1)
Pennslyvania	Hydroxy-terminated polydimethylsiloxane (70131-67-8) Stoddard Solvent (8052-41-3) Aluminatrihydrate (21645-51-2) Polydimethylsiloxane (63148-62-9) Treated silica (67762-90-7) Methyl oximino silane (22984-54-9) Methanol (67-56-1)

#### Section 16. Other Information

Revision Date Disclaimer

#### 5/19/2015

The data contained herein is based upon information that SOUDAL Accumetric believes to be reliable. Users of this product have the responsibility to determine that suitability of use and to adopt all necessary precautions to ensure the safety and protection of property and persons involved in said use. All statements or suggestions are made without warranty, expressed or implied, regarding the accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof.