

BOSS[®] 338 Flexible Gun Foam

TYPICAL PROPERTIES

Skin-over Time (1" bead).....	6 minutes (68°F & 65% R.H.)
Tack Free (1" bead).....	Dustfree after 20-25 min. at 68°F
Cure Time (1" bead)	1 hour
Tensile Strength.....	2.2 psi
Shear Strength	3.6 psi
Yield/24 Oz. Can	6.6 gallons of cured foam
Theoretical Yield - 24 oz. 1/4" bead.....	4005 ft.
Elastic Recovery (ISO 1856).....	Until 92% (75% compressed)
Acoustic Rating (EN ISO 717-1)	$R_{ST,W} (c; c_{tr}) = 60dB (-1; -4)$
Service Temperature.....	-40°F to 194°F
Application Temperature	-13°F to 120°F

*Information on this data sheet is subject to change without notice and should not be used for writing specifications.
For additional information on specific applications, contact Soudal Accumetric.



DESCRIPTION

BOSS[®] 338 Flexible Gun Foam is a one-component, moisture curing and low expansion, ready to use polyurethane foam. It has an extremely high elastic recovery and a very high Acoustic Rating and Thermal Insulation value. It also contains CFC-free propellants, which are completely harmless to the ozone layer.

BOSS[®] 338 Flexible Gun Foam has a minimal expansion after application (less than 50%). It follows joint movements, does not crack, thus maintaining its insulating properties for years, and is therefore very economical to use.

USES

- Ideal for restricting air, sound, dirt, and water vapor
- Sealing around door and window frames
- Sealing around pipes, vents and electrical outlets
- Filling joints and insulating wall panels
- Filling gaps under corrugated sheets or roof tiles



FEATURES

- Very high elastic recovery
- Copes with extreme mechanical movement without cracking
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation performance
- Very good filling capacities
- Excellent stability (no shrink or post expansion)
- Very precise application due to the foam applicator gun system
- Low expansion
- Good compressibility

HOW TO USE

BOSS® 338 may be applied to all substrates except PE and PP. Apply to surfaces that are clean and free of dust and grease. Moistening of the surfaces improves adhesion, curing and denser cellular structure. **Shake can well before use**, attach foam gun and adjust screw. For best results, use in temperatures between 60°F and 100°F and at relative humidity of 40%. Clean with BOSS® 335 Gun and Foam Cleaner before curing.

DANGER!

EXTREMELY FLAMMABLE. CONTENTS UNDER PRESSURE. Turn off all pilot lights, electrical igniters, burners and other sources of ignition or heat during use. Do not smoke, use matches or lighters while dispensing foam. Do not expose to direct sunlight, high heat or store in enclosed vehicle. Avoid breathing vapor/spray. Use only outdoors or in a adequately ventilated area with appropriate breathing apparatus. Avoid contact with skin and eyes. Wearing eyewear and gloves is recommended. Do not incinerate or puncture can. Store at temperatures below 120°F. **KEEP OUT OF REACH OF CHILDREN.** For safe handling information on this product, consult the Safety Data Sheet (SDS).

FIRST AID: In case of eye contact, flush immediately with water for 15 minutes and get medical help. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. If swallowed, drink large quantities of water. DO NOT induce vomiting. GET PHYSICIAN ASSISTANCE IN ALL CASES. Cured foam is not harmful to health.

CLEAN UP

Uncured sealant can be easily removed using a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS® Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

COLOR

BOSS® 338 Flexible Gun Foam is tan in color.

SHIPPING LIMITATIONS

Ground shipments only. Cannot ship by air.
Reactive VOC 149 g/l (16% wt)

SPECIFICATIONS

ASTM E-2112 - Standard practice for installation of exterior windows, doors and skylights (conform or results)	Conforms
ASTM E-331 - (2009) Standard test method for water penetration of exterior windows, skylights, doors and curtain walls by uniform static air pressure difference (conform or results)	Conforms
ASTM C-1620 - Standard specification for aerosol polyurethane and aerosol latex foam sealants (conform or results)	Conforms
ASTM E-84 UL 723	Flame Spread 15 Smoke Developed 35
AAMA 812 - 04 Voluntary practice for assessment of single component aerosol expanding polyurethane foams for sealing rough opening of fenestration installations	AAMA Tested and listed in the verified component list

PACKAGING

BOSS® 338 Flexible Gun Foam is available in 24 oz. can.

STORAGE AND SHELF LIFE

When stored upright in a dry environment at or below 70°F (21°C), **BOSS® 338** has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the cap pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Soudal Accumetric's control, we can accept no liability for the results obtained. Soudal Accumetric's sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Soudal Accumetric will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

BOSS® PRODUCTS

Soudal Accumetric

350 Ring Road / Elizabethtown, KY 42701 USA

800-928-BOSS(2677)

TEL (270)769-3385 / FAX (270)765-2412

Outside U.S.

TEL +1(270)769-3385 / FAX +1(270)765-2412

www.bossproducts.com