



# BOSS<sup>®</sup> 9567 Pipe Sealant with PTFE

### TYPICAL PROPERTIES

#### Uncured

Color ..... White  
 Specific Gravity (g/cc) ..... 1.05  
 Particle Size ..... 40 Micron  
 Viscosity ..... 450,000 cps  
 Flash Point ..... 860°F  
 Temperature Range ..... -65°F to 300°F  
 Storage Stability ..... + 12 months @ <75°F

#### Cured

Cure Speed ..... 4 Hours  
 Locking Torque ..... 500 in.-lbs. (1/2" NPT Pipe)  
 Instant Sealing ..... ->200 psig  
 Chemical Resistance ..... Excellent  
 Pressure Resistance ..... 10,000 psi

\*Information on this data sheet is subject to change without notice and should not be used for writing specifications.  
 For additional information on specific applications, contact Accumetric, LLC



### DESCRIPTION

**BOSS<sup>®</sup> 9567** Pipe Sealant with PTFE merges the high performance of an anaerobic sealant with the lubricity of PTFE to form a dependable, highly chemical resistant, single component sealant. **BOSS<sup>®</sup> 9567** is packaged in convenient 50ml and 250ml tubes with a flip top, ribbon applicator that allows for faster, more uniform application.

### FEATURES

- Seals all metals including stainless steel and aluminum
- Needs no primer
- Acts as a lubricant for parts during assembly
- Allow 30 minutes for readjustment of parts
- One tube provides up to 400 applications (1/8" pipe)
- Resistant to gasoline, petroleum oil, natural gas, butane and propane
- Outperforms teflon tapes
- Seals to burst rate of pipe

### PIPE SEALANT CHART

Fittings per 50ml

Pipe Diameter in inches	Manual Application
1/8" NPT .....	400
1/4" NPT .....	200
3/8" NPT .....	133
1/2" NPT .....	100
3/4" NPT .....	67
1" NPT .....	50

These figures represent typical uses and should only be used as a guideline for your specific application

## CLEAN UP

Uncured sealant can be easily removed using a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS® Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

## PACKAGING

**BOSS® 9567** is available in 50ml and 250ml tubes.

## SHIPPING LIMITATIONS

None.  
Reactive VOC 2 g/l (<1% wt)

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **BOSS® 9567** Pipe Sealant with PTFE has a shelf life of 12 months from date of shipment. In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity.

Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

## CAUTION

DIRECT CONTACT OF UNCURED PRODUCT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use with adequate ventilation. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Accumetric's control, we can accept no liability for the results obtained. Accumetric's sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Accumetric will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

## **BOSS®** PRODUCTS

**Accumetric, LLC®**  
350 Ring Road  
Elizabethtown,  
Kentucky 42701 USA  
800-928-BOSS(2677)  
TEL (270)769-3385  
FAX (270)765-2412  
*Outside U.S.*  
TEL +1 (270) 769-3385  
FAX +1 (270) 765-2412

**Accumetric Asia Pacific, LTD**  
18 Kitpanit Bldg, 5th Floor  
#502 Patpong Road  
Suriyawong, Bangrak  
Bangkok, 10500 Thailand  
TEL (662)634-3060  
FAX (662)634-3066

[www.bossproducts.com](http://www.bossproducts.com)