

PURPLE LOW STRENGTH BOLTLOCKER MEDIUM VISCOSITY PART NO. 49482

PHYSICAL PROPERTIES

Monomer (Liquid)

Base Compound Dimethacrylate Ester
 Color.....Purple
 Viscosity (cP @ 68°F) 1200 cP
 Flash Point (TCC)..... >200°F
 Gap Fill007"
 Corrosivity..... None
 Toxicity Low
 Specific Gravity (g/cc) 1.09
 Shelf Life @ 40°F 1 year unopened
 Military Specifications..... Mil-S-46163A
 Type II Grade M

Curing Properties Depends on environmental conditions and the substrates used

Polymer (Cured)

Locking Strength Low
 Service Temperature Range -75°F to 300°F
 Appearance..... Purple solid
 Shear Strength (steel nuts and bolts) 600 psi
 Full Cure Time 24 hours



DESCRIPTION

Dynatex® Purple Low Strength Boltlocker is a low strength anaerobic threadlocking material that cures between engaged threads to form a unitized assembly that resists virtually all leakage, shock and vibration. Ideal for all nut and bolt fasteners under ¼ inch. Excellent chemical resistance. Easily removable with hand tools for servicing requirements.

FEATURES

- Eliminates vibration issues
- Prevents rusting of threads
- Cures without cracking or shrinking
- Can be adjusted or disassembled
- Seals against leakage
- No torque compensation required during assembly

TYPICAL APPLICATIONS

- Small bolts in distributor
- Dash board assembly bolts
- Relay lock screws
- Idle control screws
- Small bolts in ignition systems
- Throttle body assembly bolts
- Set screw for rear view mirror

CHEMICAL RESISTANCE

Shear strength on steel after 500 hours.

Solvent	% Strength Retained
Motor Oil	100
Unleaded Gasoline	95
Trichloroethane	90
Brake Fluid	95
Ethanol	95
Acetone	95
Water/Glycol Mix	80

CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

SETTING TIME (68°F, 65% R.H.)

Substrate	Set time/Full cure
Steel	15 min/24 hrs
Brass	20 min/24 hrs

PERFORMANCE OF CURED MATERIALS

Bond strength after 24 hours at 20°C to 25°C on steel nuts and bolts

	Average Value	Range
Breakaway Torque	58 in. lbs.	25-80 in. lbs.
Prevailing Torque	30 in. lbs.	10-50 in. lbs.

GENERAL INSTRUCTIONS

Surfaces to be bonded should be clean and dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps, which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), *Dynatex® Purple Low Strength Boltlocker* has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® A division of SODAL Accumetric

Dynatex

350 Ring Road
Elizabethtown
Kentucky 42701 USA
(800) 999-2937
TEL (270) 769-5557
FAX (270) 769-6418

Outside U.S.

TEL +1(270) 769-5557
FAX +1(270) 769-6418

Email: sales@dynatexinc.com
Website: www.dynatexinc.com

Accumetric Asia Pacific, LTD

18 Kitpanit Bldg. 5th Floor
#502 Patpong Road
Suriyawong, Bangrak
Bangkok, 10500 Thailand
TEL (662) 634-3060
FAX (662) 634-3066